



# PVC GEL

## FAST, THIXOTROPIC, THF-FREE RIGID PVC CEMENT



### PRODUCT DESCRIPTION

Fast, thixotropic, THF-free rigid PVC cement.

### FIELD OF APPLICATION

For joining pipes, sockets and fittings with interference fit and loose fit (gap filling) in pressure and drainage systems. With special pipe brush for quick and easy application. Suitable for diameters  $\leq 250$  mm. Max. 16 bar (PN 16). Maximal tolerances 0.6 mm diametrical clearance / 0.2 mm press fit. Suitable for e.g. pipe systems conforming to EN 1329, 1452, 1453 and 1455.

### PROPERTIES

- THF-free
- Fast
- Does not drip
- Thixotropic
- Gap filling

### CERTIFICATES & STANDARDS

Certificates	
	Adhesive for non-pressure thermoplastic piping systems in installations for the transport/disposal/storage of water (EN 14680).
	Adhesive for thermoplastic piping systems for fluids under pressure in installations for the transport/disposal/storage of water (EN 14814).
	KIWA: Adhesives for connections in PVC and PVC/CPE water pipe systems. Approved for drinking water. Certificate K5067 based on BRL K525.
	KOMO: Adhesives for connections in non-plastified PVC interior sewage systems. Certificate K4395 based on BRL 5221.
	CSTB: Adhesives for connections in PVC piping systems. Certificate 13-AD04 (EN 14814).
	ACS: In accordance with the positive lists of ACS (Attestation de Conformité Sanitaire). Certificate Eurofins 23 CLP NY 043.
	Additif convenant aux lignes souterraines de télécommunications
	Kitemark: Solvent cement for non-pressure thermoplastic pipe systems. Licence KM 51564 (EN 14680).
	KIWA-UNI: Adhesive for thermoplastic piping systems for fluids under pressure and drinking water. Certificate KIP-097532 based on UNI EN 14814 and D.M.174.
	AENOR: Adhesivo para tubos de PVC-U para suministro de agua. Certificado No 001/006484 (EN14814).
	PZH: Hygienic Certificate B/BK/60110/1444/22.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



# PVC GEL

## FAST, THIXOTROPIC, THF-FREE RIGID PVC CEMENT

Standards	
<b>EN 14680</b>	EN 14680: Meets requirements European standard 14680: Adhesive for non-pressure thermoplastic piping systems.
<b>EN 14814</b>	EN 14814: Meets requirements European standard 14814: Adhesive for thermoplastic piping systems for fluids under pressure.

### PREPARATION

**Working Conditions:** Do not use in temperatures  $\leq +5^{\circ}\text{C}$ .

### APPLICATION

**Coverage:** Indication of the number of joints per 1 L:

Ø	32	40	50	63	75	90	110	125	160	200	250
#	650	290	160	100	90	70	40	30	20	12	8

### Directions for use:

1. Cut pipes square, chamfer edges and deburr. 2. Clean surfaces with Griffon Cleaner and Cleaner Cloth. 3. Apply adhesive rapidly and evenly all around (4-6x) on both surfaces (pipe thickly, socket thinly). 4. Assemble joint immediately. Remove excess adhesive. Do not load the joint mechanically for the first 10 minutes. Close packaging immediately after use.

**Stains/residue:** Remove adhesive stains with Griffon Cleaner and Cleaner Cloth.

**Points of attention:** Brush size varies per packaging volume. Use a suitable packaging (brush) for the diameter to be bonded.

16 - 63 mm	40 - 90 mm	50 - 160 mm	160 - 250 mm
250 ml	500 ml	1000 ml	BRUSH

### TECHNICAL SPECIFICATIONS

Chemical base:	Solution of PVC in a mixture of solvents
Chemicals resistance:	The chemical resistance of adhesive joints depends on the gap width, drying time, pressure, temperature, type and concentration of medium. The adhesive joint generally has the same chemical resistance as the material itself. Exceptions to this are a small number of very aggressive chemicals such as concentrated inorganic acids, caustic solutions and strong oxidants.
Colour:	Colourless
Density approx.:	0.89 g/cm <sup>3</sup>
Flash point:	K1 (<21°C)
Temperature resistance:	40 °C
Temperature resistance, peak load:	95 °C
Solid matter approx.:	21 %
Viscosity:	Thixotropic
Viscosity approx.:	1200 mPa·s

Ø	16 – 63 mm		75 – 110 mm		125 – 250 mm		16 – 250 mm
°C	10 BAR	16 BAR	10 BAR	16 BAR	10 BAR	16 BAR	DRAINAGE
5°C - 10°C	4 hour	8 hour	8 hour	16 hour	16 hour	32 hour	2 hour
>10°C	2 hour	4 hour	4 hour	8 hour	8 hour	16 hour	1 hour

\* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

### STORAGE CONDITIONS

Shelf life: At least 18 months after production.

Stored in unopened packaging between +5°C and +25°C.

Best Before Date (MM/YY): see packaging. Close packaging properly after use and store in a dry, cool, and frost-free location.

Limited shelf life after opening.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.