



POLY MAX® SEALANT ALL JOINTS

PREMIUM QUALITY, MULTIFUNCTIONAL SEALANT BASED ON INNOVATIVE HYBRID SMP-TECHNOLOGY



PRODUCT DESCRIPTION

GRIFFON Poly Max® Sealant All Joints is a premium quality, multifunctional sealant for sealing applications in sanitary-, interior- & exterior areas.

FIELD OF APPLICATION

Suitable for waterproof sealing of joints, gaps and seams in sanitary & kitchen applications such as (synthetic) shower cabinet, walk-in showers, bath tubs, sinks, toilets, joints between the kitchen counter, tiled walls and floors. Can be applied (without primer) on almost all (even on moist) construction materials such as concrete, bricks, drywall, masonry, ceramics, glass, ceramic & enameled tiles, granite, (disbarked) wood, stainless steel and many other metals and synthetics. Also suitable for shrink-free sealing of strong moving joints and dilatation joints, seams and cracks in constructions, walls and ceilings as well for sealing connecting joints along door- and window frames, windowsills, skirting boards and stairs. Not suitable for bitumen, polyethylene (PE), polypropylene (PP), PTFE, copper based metals (bronze, brass) and not suitable for glazing applications and aquaria.

PROPERTIES

- Permanent elastic
- Mildew resistant
- Does not shrink
- Paintable with most water-based paint systems
- Very good adhesion on many (even moist) surfaces
- Can be used outdoors due to excellent weather- & UV resistance
- Easy to process and smoothen

- Fast curing, sanitary areas can be used after 2 hours (=water resistant) and immediately resistant to (light) rain.
- Non tacky
- Free of solvents, isocyanates and silicone
- (Sea) water & chemical resistant and resistant to all commonly used detergents
- No bladder formation, even in hot and humid weather
- Acid-free & not corrosive to metals
- Neutral curing system; almost odorless

CERTIFICATES & STANDARDS

Certificates



EMICODE: Classification system (GEV) of emission properties for construction products in indoor areas. EC-1 Plus (Very low emission Plus)

PREPARATION

Working Conditions: Application temperature: +5°C to +40°C. The optimum processing temperature for cartridge and surface is between 15°C and 25°C.

Surface Requirements: Surfaces must be clean, free of dust, rust- and grease. Surface must be solid. The surface may be slightly moist. Use of a primer not required.

Preliminary Surface Treatment: If necessary, prevent three-sided bonding by filling the joint with a foam backer rod or PE film.

Tools: GRIFFON Professional Cartridge Gun, GRIFFON Multitool, GRIFFON Sealant Finisher, GRIFFON Sealant Finishing Tool, GRIFFON Wipes.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



POLY MAX® SEALANT ALL JOINTS

PREMIUM QUALITY, MULTIFUNCTIONAL SEALANT BASED ON INNOVATIVE HYBRID SMP-TECHNOLOGY

APPLICATION

Coverage: Suitable for approximately 15 meters x 5 mm joint.

Directions for use:

Surface must be clean, free of dust and grease. Cut open cartridge up to the thread with GRIFFON Multitool or sharp box cutter. Turn the nozzle onto the cartridge. Cut the nozzle to the desired diameter (= joint width) (at least 5 mm Ø in case of joint seams). Place cartridge in the sealant gun and inject sealant evenly into the joint, crack or hole. Keep the nozzle tight onto the joint to make sure the sealant is applied into the joint. Spray Sealant Finisher onto the joint. Moisten Joint Tool and smoothen sealant within 10 - 15 minutes. Let the sealant fully cure. After approx. 15 minutes, a surface skin will form.

Stains/residue: Remove excess sealant residues immediately with a wet cloth or GRIFFON Wipes, remove cured sealant residues mechanically or with GRIFFON Silicone Remover.

Advice:

- Ensure a minimum joint width of 5 mm and a maximum of 25 mm. The joint depth depends on the joint width. The joint depth should always be in the correct relationship of the joint width.
- Joint - Depth calculation joints < 9mm : Joint Depth = Joint Width
- Joint - Depth calculation joints > 9mm : Joint Depth = (Joint Width / 3) + 6mm
- GRIFFON Poly Max® Sealant All Joints cures under the influence of humidity. Contact with humidity is therefore absolutely necessary during curing.

Points of attention:

- Shower can be used after 2 hours (water resistant joint). Caution: do not immediately fully load shower cabinet or bath!
- For bonding applications, use GRIFFON Poly Max® Pro Power or GRIFFON Poly Max® Fix & Seal.
- Can be painted with all Acrylic and most Alkyd paints. Tip: Given the wide variety of paints, always check paint compatibility on sealant in advance. For the best results it's recommended to paint after 2 hours.
- Take into account that curing time of Alkyd paints may take longer.
- Total UV absence can cause discoloration of the sealant. Possible discoloration does not affect the technical properties of the sealant.
- Due to the variety of substrates (e.g. metals, plastics, etc.), it is recommended to carry out a material compatibility- and adhesion test in case of doubt.

TECHNICAL SPECIFICATIONS

100% modulus:	0.6 MPa
Chemical base:	SMP Polymer
Chemicals resistance:	Very good
Cure rate:	2.5 mm/24h
Density approx.:	1.43 g/cm ³
Elasticity:	Very good
Elongation of rupture:	300 %
Filling capacity:	Very good
Hardness (Shore A):	38
Minimum temperature resistance:	-40 °C
Maximum temperature resistance:	100 °C
Mildew resistance:	Very good
Overpaintable after:	2 hrs
Skinover time:	10-15 minutes
Tensile strength (N/cm ²) approx.:	150 N/cm ²
RAL Colour Code:	Close to RAL 7016

STORAGE CONDITIONS

Store closed cartridge in a dry (between 5 - 25°C) place. Shelf Life: 18 months (after production date). Limited shelf life after opening.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.