

# **KOLMAT® EASYFIT**

## ANAEROBIC SEALANT AND SECURING AGENT



#### PRODUCT DESCRIPTION

Anaerobic sealant and securing agent for conical and cylindrical metal threaded connections.

#### FIELD OF APPLICATION

Suitable for, e.g., cold and warm water (CH), steam, gas, oil, glycol, diluted acids and bases, various solvents and fuels, and (compressed) air. Can be applied to copper, brass, (galvanized) steel and stainless steel amongst other materials. Suitable for diameters  $\leq$  4" (ISO 7-1). Maximum clearance 0.35 mm. Not suitable for concentrated acids and bases and oxygen.

#### **PROPERTIES**

- · Immediately loadable at low pressure
- · Resistant to thermal shock and vibration
- · Chemical resistant

#### **CERTIFICATES & STANDARDS**

#### **Certificates**



Gastec QA: Screw thread sealant for gas-tight sealing of metal threaded pipe joints, class 8 bar. Certificate Q 014/006 based on GASTEC QA demands 31-2.



ACS: In accordance with the positive lists of ACS (Attestation de Conformité Sanitaire). Certificate Eurofins 20 CLP NY 007.



DVGW: Sealing product for threaded connections in gas-und water installations. Certificate NG-5146BT107

#### Standards



EN 751-1 (H): Sealing materials for metallic threaded joints in contact with 1st, 2nd and 3rd family gasses and hot water. Part 1 Anaerobic compounds.

#### **PREPARATION**

**Working Conditions:** Do not use in temperatures  $\leq +5^{\circ}$ C. **Preliminary Surface Treatment:** Clean surfaces using a degreaser (Griffon Primor) and a clean, well-absorbent lint-free cloth (Griffon Cleaner Cloth).

#### **APPLICATION**

#### **Directions for use:**

1. Clean surfaces using a degreaser (Griffon Primor) and a clean, well-absorbent lint-free cloth (Griffon Cleaner Cloth).
2. Apply evenly to the first 4 screw threads of the male part and the first screw thread of the female part. 3. Assemble joint immediately and remove residue. Curing time (>20°C): functional 3 - 6 hours, final 12 - 24 hours (except stainless steel 72 hours). Difficult to detach after curing.

**Stains/residue:** Remove any residue with a moist cloth or degreaser.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



# **KOLMAT® EASYFIT**

# **ANAEROBIC SEALANT AND SECURING AGENT**

### **TECHNICAL SPECIFICATIONS**

TECHNICAL SPECIFICATIONS	
Chemical base:	Methacrylate ester
Chemicals resistance:	Good
Colour:	Yellow
Density approx.:	1,08 g/cm <sup>3</sup>
Final bond strength after:	24 hours
Max. bonding gap:	0.35 mm
Minimum application temperature:	5 °C
Maximum application temperature:	40 °C
Minimum temperature resistance:	-50 °C
Maximum temperature resistance:	150 °C
Viscosity approx.:	20000 mPa·s
Water resistance:	Very good

### **STORAGE CONDITIONS**

A minimum of 24 months. Limited shelf life after opening.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.